

Galvanised Ropes: 4x36 Fibre Core

BS EN 12385

Finish: Galvanised

1960N Tensile Grade

Normal Diameter (mm)	Approx Mass (kg/100m)	Min Breaking Load (tonnes)	Min Breaking Force (kN)
9.3	34	6.75	66.19

