


Galvanised Ropes: 6x19 Fibre Core

BS EN 12385
Finish: Galvanised

1960N Tensile Grade



Normal Diameter (mm)	Approx Mass (kg/100m)	Min Breaking Load (tonnes)	Min Breaking Force (kN)
6	12.9	2.38	23.3
7	17.1	3.23	31.7
8	23.0	4.22	41.4
9	29.1	5.34	52.4
10	35.9	6.60	64.7
11	43.3	7.99	78.3
12	51.7	9.50	93.1
13	60.7	11.10	109.0
14	70.4	13.00	127.0
16	91.9	16.90	166.0

