


Galvanised Ropes: 6x25 IWRC

BS EN 12385

Finish: Galvanised

1960N Tensile Grade



Normal Diameter (mm)	Approx Mass (kg/100m)	Min Breaking Load (tonnes)	Min Breaking Force (kN)
10	40.0	7.12	69.8
11	48.4	8.61	84.4
12	57.6	10.20	100.0
13	67.6	12.00	118.0
14	78.4	14.00	137.0
16	102.0	18.30	179.0
18	130.0	23.10	226.0
19	144.0	25.70	252.0
20	160.0	28.50	279.0
21	176.0	31.40	308.0
22	194.0	34.50	338.0
24	230.0	41.00	402.0
26	270.0	48.10	472.0
28	314.0	55.80	547.0
29	336.0	59.90	587.0
32	410.0	72.90	715.0
35	490.0	87.20	855.0
36	518.0	92.20	904.0
38	578.0	103.00	1010.0
40	640.0	114.00	1120.0
44	774.0	138.00	1350.0
48	922.0	164.00	1610.0
52	1080.0	193.00	1890.0



Lifting Equipment
Engineers Association

