


Galvanised Ropes: 6x36 IWRC

BS EN 12385

Finish: Galvanised

1960N Tensile Grade



Normal Diameter (mm)	Approx Mass (kg/100m)	Min Breaking Load (tonnes)	Min Breaking Force (kN)
8	26.2	4.56	44.7
9	33.1	5.76	56.5
10	40.9	7.12	69.8
11	49.5	8.61	84.4
12	58.9	10.20	100.0
13	69.1	12.00	118.0
14	80.2	14.00	137.0
16	105.0	18.30	179.0
18	133.0	23.10	226.0
19	148.0	25.70	252.0
20	164.0	28.50	279.0
22	198.0	34.50	338.0
24	236.0	41.00	402.0
26	276.0	48.10	472.0
28	321.0	55.80	547.0
32	419.0	72.90	715.0
35	501.0	87.20	855.0
36	530.0	92.20	904.0
38	591.0	103.00	1010.0
40	654.0	114.00	1120.0
44	792.0	138.00	1350.0
48	942.0	164.00	1610.0
52	1110.0	193.00	1890.0
54	1190.0	208.00	2040.0



Lifting Equipment
Engineers Association

