

Galvanised Ropes 6x7 Fibre Core

BS EN 12385
Finish: Galvanised

1960N Tensile Grade

Normal Diameter (mm)	Approx Mass (kg/100m)	Min Breaking Load (tonnes)	Min Breaking Force (kN)
2	1.38	0.24	2.35
3	3.11	0.54	5.29
4	5.54	0.96	9.40
5	8.65	1.50	14.70
6	12.50	2.16	21.20
7	17.00	2.94	28.80

